

Auditing Test Report

Test Report No.: SA13-4043/29

Date: 10/01/2024

Client

Saudi Vitrified Clay Pipe Co.
P.O. Box 6415
Riyadh 11442
Kingdom of Saudi Arabia

Sampling Date: 06/01/2024

Test Date: 07/01/2024

Auditing Purpose:

Testing of Vitrified Clay Pipes jointed by system C according to EN 295-1:2013

Size Description:

Nominal Size: DN 300 * 2000 mm
Jointing System: System C
Class: 240 - Class A

Description of Sampling

Samples were collected randomly from the stock at the client's manufacturing works in Riyadh (Kingdom of Saudi Arabia) by the agent of the Suhaimi - Fugro

Underlying specification /description of the tests

EN 295-1:2013	"Vitrified clay pipe systems for drains and sewers - Part 1: Requirements for pipes, fittings & joints"
GSO EN 295-1:2008	"Vitrified clay pipe systems for drains and sewers - Part 1: Requirements for pipes, fittings & joints"
EN 295-2:2013	"Vitrified clay pipe systems for drains and sewers - Part 2: Evaluation of conformity and sampling"
EN 295-3:2012	"Vitrified clay pipe systems for drains and sewers - Part 3: Test Methods"



Test Results of DN 300 ES - Class A

Test Report No.: SA13-4043/29

Test Type		Unit	Sample 1	Sample 2	Sample 3	Req.	Result	
Pipes	Marking (visual Inspection)	-	✓	✓	✓	✓	✓	
	Crushing Strength	KN/m	88	91	95	≥ 72	✓	
	Internal Barrel Diameter "D1"	mm	300	300	302	≥ 293	✓	
	Length	mm	2010	2000	2005	2000 ^{+4%} _{-1%}	✓	
	Water Tightness	L/m ²	0.02	0.01	0.02	≤ 0.04	✓	
	Deviation from Straightness	mm	0.6	0.8	0.5	< 4.0	✓	
	Squareness of Ends	Socket	mm	2.5	2.4	2.6	< 6.0	✓
		Spigot	mm	2.4	2.3	2.1		
	Airtightness	mm	10	10	5	Drops ≤ 25	✓	
	Chemical Resistance	%	0.15	0.16	0.15	0.10-0.25%	✓	
Water Absorption	%	2.9	2.8	2.8	≤ 6%	✓		
Joint Assembly	Joint Interchangeability (D4)	mm	398.8	398.9	398.9	398.5 ± 0.5	✓	
	Watertightness under Angular Deflection	0.5 bar	No leak, Deflection applied is 30 mm/m for 5 min.			No visible leakage	✓	
	Watertightness under Shear	0.5 bar	No leak, Shear force applied is 7.5 KN for 15 min.			No visible leakage	✓	
	Continuity of Invert	mm	2.7	2.7	2.4	≤ 4	✓	

FUGRO - SUHAIMI LTD

Mohammad Afaq

