

Auditing Test Report

Date: 06/07/2018

Lab No. : 40329-21

Jab No.: SA13-4043

Client

Saudi Vitrified Clay Pipe Co.
P.O. Box 6415
Riyadh 11442
Kingdom of Saudi Arabia

Sampling Date:

03/07/2018

Testing Date:

05/07/2018

Auditing Purpose:

Testing of Vitrified Clay Pipes jointed by system C according to EN 295-1:2013

Size Description:

Nominal Size: **DN 600 * 2000 mm**
Jointing System: **System C**
Class: **160**

Description of Sampling

Samples were collected randomly from the stock at the client's manufacturing works in Riyadh (Kingdom of Saudi Arabia) by the agent of the Suhaimi - Fugro


Underlying specification /description of the tests

EN 295-1:2013	"Vitrified clay pipe systems for drains and sewers - Part 1: Requirements for pipes, fittings & joints"
GSO EN 295-1:2008	"Vitrified clay pipe systems for drains and sewers - Part 1: Requirements for pipes, fittings & joints"
EN 295-2:2013	"Vitrified clay pipe systems for drains and sewers - Part 2: Evaluation of conformity and sampling"
EN 295-3:2012	"Vitrified clay pipe systems for drains and sewers - Part 3: Test Methods"



Test Results

	Test Type		Unit	Sample 1	Sample 2	Sample 3	Req.	Result
	Pipes	Marking (visual Inspection)		-	✓	✓	✓	✓
Crushing Strength		KN/m	115	109	118	≥ 96	✓	
Internal Barrel Diameter "D1"		mm	604	606	603	≥ 585	✓	
Length		mm	2010	2005	2010	2000 ^{+4%} _{-1%}	✓	
Water Tightness		L/m ²	0.023	0.017	0.025	≤ 0.04	✓	
Deviation from Straightness		mm	1.1	0.6	0.8	< 3.0	✓	
Squariness of Ends		Socket	mm	4.4	5.7	5.2	< 12.0	✓
		Spigot	mm	6.7	6.9	6.5		
Airtightness		mm	12	17	19	Drops ≤ 25	✓	
Water Absorption		%	4.4	5.1	4.9	≤ 6 %	✓	
Joint Assembly	Joint Interchangeability		mm	758.3	758.0	758.2	758 ± 0.5	✓
	Watertightness under Angular Deflection		-	No leak, Deflection applied is 20 mm/m for 5 min.			No visible leakage	✓
	Watertightness under Shear		-	No leak, Shear force applied is 15.0 KN for 15 min.			No visible leakage	✓
	Continuity of Invert		mm	3.8	2.9	3.3	≤ 6.0	✓



FUGRO - SUHAIMI LTD

ANIL K MATHEW

