

## Auditing Test Report

Lab No. : 40357

Date: 12/9/2018

Job No: SA13-4043

### Client

Saudi Vitrified Clay Pipe Co.  
P.O. Box 6415  
Riyadh 11442  
Kingdom of Saudi Arabia

### Sampling Date:

05 September 2018

### Testing Date:

11 September 2018

### Auditing Purpose:

Testing of Chemical and physical resistance to effluent of joint assemblies according to EN 295-1:2013, Clause 6.5

Testing of Thermal cycling stability of joint assemblies according to EN 295-1:2013, Clause 6.6

Testing of Long-term thermal stability of joint assemblies according to EN 295-1:2013, Clause 6.7

### Description of Sampling

Samples were taken from the stock at the client's manufacturing works in Riyadh (Kingdom of Saudi Arabia) by the agent of the Suhaimi - Fugro

### Underlying specification of the tests


EN 295-1:2013 "Vitrified clay pipe systems for drains and sewers - Part 1: Requirements for pipes, fittings & joints"

EN 295-2:2013 "Vitrified clay pipe systems for drains and sewers - Part 2: Evaluation of conformity and sampling"

EN 295-3:2012 "Vitrified clay pipe systems for drains and sewers - Part 3: Test Methods"



Test	Requirements	Pipe Size	Chemical Solution	PH	Water tightness Result
Chemical Resistance to effluent for joint assemblies	Four joint assemblies shall be immersed in different four chemical solutions for 168 hrs, then water tightness shall be carried out and there shall be no visible leakage within 5 min.	250 SS	H <sub>2</sub> SO <sub>4</sub>	2.0	No visible leakage
		250 SS	HNO <sub>3</sub>	2.0	No visible leakage
		250 SS	NaOH	12.0	No visible leakage
		250 SS	NaOCl	12.0	No visible leakage
Thermal Cycling	Joint Assmebly shall withstand cyclic temperature changes between (-10) °C and (+70) °C without visible defect. Then, water tightness shall be carried out for the same joint assembly for 15 min. and there shall be no visible leakage	150 mm	-	-	No visible leakage
		250 SS	-	-	No visible leakage
Long Term Thermal Cycling	Water shall be fed through a joint assembly to maintain a temperature of (45) °C for seven days. A watet tightness shall be then carried out for the same assmebly for 15 min. and there shall be no visible leakage.	250 SS	-	-	No visible leakage

  
 FUGRO - SUHAIMI LTD  
 ANIL K MATHEW

