

**Auditing Test Report** 

Date:

10/01/2024

Report No.: SA13-4043/7

Client

Sampling Date:

06/01/2024

Saudi Vitrified Clay Pipe Co.

P.O. Box 6415

Test Date:

07/01/2024

Riyadh 11442

Kingdom of Saudi Arabia

**Auditing Purpose:** 

Testing of Perforated Vitrified Clay Pipes jointed by system C according to EN 295-5:2013

**Size Description:** 

Nominal Size:

DN 400 SS \* 2000 mm Locally Perforated

Jointing System:

System C

Class:

120

## **Description of Sampling**

Samples were collected randomly from the stock at the client's manufacturing works in Riyadh (Kingdom of Saudi Arabia) by the agent of the Suhaimi - Fugro

## Underlying specification /description of the tests

EN 295-1:2013 "Vitrified clay pipe systems for drains and sewers - Part 1: Requirements for pipes, fittings & joints"

EN 295-5:2013 "Vitrified clay pipe systems for drains and sewers - Part 5: Requirements for pipes & fittings"

EN 295-2:2013 "Vitrified clay pipe systems for drains and sewers - Part 2: Evaluation of conformity and sampling"

EN 295-3:2012 "Vitrified clay pipe systems for drains and sewers - Part 3: Test Methods

ين درويت المحتوال ال



## **Test Results of DN 400 SS LP**

Report No.: SA13-4043/7

|                | Test Type                     | Unit  | Sample 1 | Sample 2 | Sample 3 | Req.         | Result    |
|----------------|-------------------------------|-------|----------|----------|----------|--------------|-----------|
| Pipes          | Marking (visual Inspection)   | -     | <b>√</b> | <b>✓</b> | ✓        | <b>✓</b>     | /         |
|                | Crushing Strength             | KN/m  | 70       | 73       | 72       | ≥ 64         | ~         |
|                | Internal Barrel Diameter "D1" | mm    | 405      | 402      | 406      | ≥ 390        | ~         |
|                | Length                        | mm    | 2005     | 2015     | 2010     | 2000 +5% -2% | ~         |
|                | Deviation from Straightness   | mm    | 2.4      | 2.1      | 2.1      | < 4.0        | ~         |
|                | Perforation Area              | mm²/m | -        | 13133.8  |          | ≥ 1200       | · /       |
|                | Water Absorption              | %     | 4.9      | 4.6      | 4.8      | ≤6%          | ~         |
| Joint Assembly | Joint Interchangeability      | mm    | 483.6    | 483.7    | 483.8    | 483.5 ± 0.5  | . 3. 10 5 |
|                | Continuity of Invert          | mm    | 2.5      | 2.6      | 2.4      | ≤ 4          | 1         |

FUGRO SUHAIMI LTD

**Mohammad Afaq** 

