

Auditing Test Report

Date: 12/7/2017

Lab No. : 40155-11

Client

Saudi Vitrified Clay Pipe Co.
P.O. Box 6415
Riyadh 11442
Kingdom of Saudi Arabia

Sampling Date:

10/7/2017

Testing Date:

11/7/2017

Auditing Purpose:

Testing of Perforated Vitrified Clay Pipes jointed by system C according to EN 295-5:2013

Size Description:

Nominal Size: **DN 600 * 2000 mm Half Perforated**
Jointing System: **System C**
Class: **160**

Description of Sampling

Samples were collected randomly from the stock at the client's manufacturing works in Riyadh (Kingdom of Saudi Arabia) by the agent of the Suhaimi - Fugro

Underlying specification /description of the tests

EN 295-1:2013	"Vitrified clay pipe systems for drains and sewers - Part 1: Requirements for pipes, fittings & joints"
EN 295-5:2013	"Vitrified clay pipe systems for drains and sewers - Part 5: Requirements for pipes & fittings"
EN 295-2:2013	"Vitrified clay pipe systems for drains and sewers - Part 2: Evaluation of conformity and sampling"
EN 295-3:2012	"Vitrified clay pipe systems for drains and sewers - Part 3: Test Methods"



Test Results

	Test Type	Unit	Sample 1	Sample 2	Sample 3	Req.	Result
Pipes	Marking (visual Inspection)	-	✓	✓	✓	✓	✓
	Crushing Strength	KN/m	110.5	111.2	102	≥ 96	✓
	Internal Barrel Diameter "D1"	mm	602	599.7	600	≥ 585	✓
	Length	mm	2003	2003	2010	2000 ^{+5%} _{-2%}	✓
	Deviation from Straightness	mm	0.6	0.2	0.4	< 3.0	✓
	Perforation Area	mm ² /m		10215.2		≥ 1800	✓
	Water Absorption	%	5.5	5.6	5.1	≤ 6 %	✓
Joint Assembly	Joint Interchangeability	mm	758.4	757.9	758.2	758 ± 0.5	✓
	Continuity of Invert	mm	4.1	4.5	4.3	≤ 6.0	✓
	Chemical Resistant	% loss	0.19% & 0.21%, Two test pieces have been immersed totally in 500 ml of H ₂ SO ₄ & NaOH solutions for 48 h at a temperature of (20 ± 5) °C			0.1% to 0.25%	✓


FUGRO - SUHAIMI LTD

Anil K Mathew

