

**TEST REPORT**

**TENSILE AND ELONGATION PROPERTIES OF RUBBER MATERIAL**


ASTM D412 / ISO 527-3

Customer	Saudi Vetrified Clay Pipe Co.Ltd.	Sample Description	Rubber Poly-Urethane 2 mm thickness
Project Name	Internal Quality	Sample Source	Saudi Vetrified Clay Pipe Co.Ltd
Project No.	NP	Sampling Method	NP
Location	Riyadh, KSA	Sampling Date	25-Oct-20
Contractor	NP	Sampled by	Customer.
Consultant	NP		
CBML Project No.	CBMP-0177-18	Date Received	25-Oct-20
CBML Sample No.	CBM-251020-002	Sample Condition	Normal
CBML Report No.	CBMR-20-02675	Environmental Condition	Room Temperature
Date of Report	25-Oct-20	Date of Test	25-Oct-20
Material Desc.	Rubber Poly-Urethane 2 mm thickness	Customer Identification	1, 2 & 3
Manufacturer	Saudi Vetrified Clay Pipe Co.Ltd.	Sampled Location	SPIGOT Rubber
Production Date	24-Oct-20	Sample Brought in by	Customer.
Sample Size	3 Qty	Batch No	NP


**Test Results**

CBML Specimen No.	1	2	3	Average	Specification Limits
Width of Specimen mm	6.01	6.09	6.04	6.05	
Thickness of Specimen mm	2.01	2.05	2.01	2.02	
Ultimate Tensile Strength (R <sub>m</sub> ) MPa	3.57	4.53	3.16	3.75	Min. 2.00
Elongation at Fracture %	139	143	119	134	Min. 90

Tested by : SBT  
Test Variation : NIL  
Remarks : NIL



**AUTHORIZED SIGNATORY**



CBMR-031 Rev. 0  
Result related to the items tested.  
This test report shall not be reported except in full, without the written approval of the laboratory.

Kingdom of Saudi Arabia  
P.O.Box 88458 Riyadh 11662  
Phone: +966 920029293  
Fax: +966 920029296  
Membership No.: 174400  
C.R.No. 1010225110

Closed Shareholding Co.: Fully Paid Capital: S.R. 500.000.000

للإتصال من خارج المملكة.  
هاتف : +966 1 4160110  
فاكس : +966 1 4160497

www.motabaqah.com.sa

المملكة العربية السعودية  
ص.ب 88458 الرياض 11662  
هاتف : +966 920029293  
فاكس : +966 920029296  
رقم العضوية : 174400  
السجل التجاري : 1010225110  
شركة مساهمة مقفلة برأس مال : 500.000.000 ر.س (مدفوع بالكامل)