

Auditing Test Report

Test Report No.:SA13-4043-26

Date: 01/08/2021

Client

Saudi Vitrified Clay Pipe Co.

P.O. Box 6415

Riyadh 11442

Kingdom of Saudi Arabia

Sampling Date: 28/07/2021

Test Date: 29/07/2021

Auditing Purpose:

Testing of Vitrified Clay Pipes jointed by system C according to EN 295-1:2013

Size Description:

Nominal Size: DN 300 * 2000 mm

Jointing System: System C


Class: 240

Description of Sampling

Samples were collected randomly from the stock at the client's manufacturing works in Riyadh (Kingdom of Saudi Arabia) by the agent of the Suhaimi - Fugro

Underlying specification /description of the tests

EN 295-1:2013	"Vitrified clay pipe systems for drains and sewers - Part 1: Requirements for pipes, fittings & joints"
GSO EN 295-1:2008	"Vitrified clay pipe systems for drains and sewers - Part 1: Requirements for pipes, fittings & joints"
EN 295-2:2013	"Vitrified clay pipe systems for drains and sewers - Part 2: Evaluation of conformity and sampling"
EN 295-3:2012	"Vitrified clay pipe systems for drains and sewers - Part 3: Test Methods"



Test Results of DN 300 ES

Test Report No.:SA13-4043-26

Test Type		Unit	Sample 1	Sample 2	Sample 3	Req.	Result	
Pipes	Marking (visual Inspection)	-	✓	✓	✓	✓	✓	
	Crushing Strength	KN/m	101	88	83	≥ 72	✓	
	Internal Barrel Diameter "D1"	mm	301	300	302	≥ 293	✓	
	Length	mm	2010	2010	2005	2000 ^{+4%} _{-1%}	✓	
	Water Tightness	L/m ²	0.02	0.03	0.02	≤ 0.04	✓	
	Deviation from Straightness	mm	1.1	1.4	2.1	< 4.0	✓	
	Squareness of Ends	Socket	mm	2.2	2.4	1.9	< 6.0	✓
		Spigot	mm	2.4	1.8	2.1		
	Airtightness	mm	11	11	9	Drops ≤ 25	✓	
	Water Absorption	%	3.4	2.1	3.4	≤ 6 %	✓	
Joint Assembly	Joint Interchangeability	mm	398.7	398.9	398.9	398.5 ± 0.5	✓	
	Watertightness under Angular Deflection	-	No leak, Deflection applied is 30 mm/m for 5 min.			No visible leakage	✓	
	Watertightness under Shear	-	No leak, Shear force applied is 7.5 KN for 15 min.			No visible leakage	✓	
	Continuity of Invert	mm	2.7	2.8	2.4	≤ 4	✓	

FUGRO - SUHAIMI LTD

Neesar Ahmed

