

**TEST REPORT**

**TENSION TESTING OF RUBBER MATERIALS**  
ASTM D 412 / ISO 527-3


Page 1 of 1

Customer	Saudi Vetrified Clay Pipe Co.	Sample Description	Rubber Poly-Urethane 2 mm thickness
Project Name	SASO Approval	Sample Source	Saudi Vetrified Clay Pipe Co.
Project No.	NP	Sampling Method	16-Jan-20
Location	Riyadh, KSA	Sampling Date	NP
Contractor	NA	Sampled by	Customer.
Consultant	NA		
CBML Project No.	CBMP-0177-18	Date Received	16-Jan-20
CBML Sample No.	CBM-160120-019	Sample Condition	Normal
CBML Report No.	CBMR-20-00239	Environmental Condition	Room Temperature
Date of Report	19-Jan-20	Date of Test	19-Jan-20
Material Grade	NP	Customer Identification	1, 2 & 3
Production date	NP	Sampled Location	Production Line
Sample Size	3 Qty	Sample brought in by	Customer.
Manufacturer	Saudi Vetrified Clay Pipe Co.	Structural Ref.	NP

ASTM D 412 / ISO 527-3

CBML Sample No.	1	2	3	Average	Specification limits	
Customer's Ref. No.	NP					
Heat No.	NP					
Thickness of Specimen	mm	2.02	2.03	2.01	2.02	
Width of Specimen	mm	5.82	5.85	5.84	5.84	
Ultimate Tensile Strength (Rm)	MPa	2.55	2.69	2.67	2.64	Min.2.0
Elongation at Fracture	%	96	102	96	98.00	Min.90

Tested by : SBT  
Test Variation : NIL  
Remarks : NIL

  
**AUTHORIZED SIGNATORY**



CBMR-077 Rev. 0  
Result related to the items tested.  
This test report shall not be reported except in full, without the written approval of the laboratory.

Kingdom of Saudi Arabia  
P.O.Box 88458 Riyadh 11662  
Phone: +966 920029293  
Fax: +966 920029296  
Membership No.: 174400  
C. R. N.c. 1010225110

للاتصال من خارج المملكة  
هاتف : +966 1 4160110  
فاكس : +966 1 4604907  
www.motabaqah.com.sa

المملكة العربية السعودية  
ص.ب. 88458 الرياض 11662  
هاتف : +966 920029293  
فاكس : +966 920029296  
رقم العضوية : 174400  
السجل التجاري : 1010225110  
شركة مساهمة مقفلة برأس مال : 500.000.000 ر.س. (مدفوع بالكامل)

Closed Shareholding Co.: Fully Paid Capital: S.R. 500.000.000