

**TEST REPORT**

**TENSILE AND ELONGATION PROPERTIES OF RUBBER MATERIAL**


ASTM D412 / ISO 527-3

Customer	Saudi Vetrified Clay Pipe Co.Ltd.	Sample Description	Rubber Poly-Urethane 2 mm thickness
Project Name	Internal Quality	Sample Source	Saudi Vetrified Clay Pipe Co.Ltd.
Project No.	NP	Sampling Method	NP
Location	Riyadh, KSA	Sampling Date	23-Feb-20
Contractor	NP	Sampled by	Customer.
Consultant	NP		
CBML Project No.	CBMP-0177-18	Date Received	23-Feb-20
CBML Sample No.	CBM-230220-022	Sample Condition	Normal
CBML Report No.	CBMR-20-00773	Environmental Condition	Room Temperature
Date of Report	1-Mar-20	Date of Test	1-Mar-20
Material Desc.	Rubber Poly-Urethane 2 mm thickness	Customer Identification	1, 2 & 3
Manufacturer	Saudi Vetrified Clay Pipe Co.Ltd.	Sampled Location	Site
Production Date	22-Feb-20	Sample Brought in by	Customer.
Sample Size	3 Qty	Batch No	NP

**Test Results**

CBML Specimen No.	1	2	3	Average	Specification Limits
Width of Specimen mm	5.78	5.3	5.61	5.56	
Thickness of Specimen mm	2.03	2.01	2.01	2.02	
Ultimate Tensile Strength (Rm) MPa	2.81	2.84	2.94	2.86	Min. 2.00
Elongation at Fracture %	102	98	104	101.33	Min. 90

Tested by : SBT  
Test Variation : NIL  
Remarks : NIL

  
AUTHORIZED SIGNATORY



CBMR-031 Rev. 0  
Result related to the items tested.  
This test report shall not be reported except in full, without the written approval of the laboratory.

Kingdom of Saudi Arabia  
P.O.Box 88458 Riyadh 11662  
Phone: +966 920029293  
Fax: +966 920029296  
Membership No.: 174400  
C. R. No. 1010225110

Closed Shareholding Co.: Fully Paid Capital: S.R. 500.000.000

للاتصال من خارج المملكة  
هاتف : +966 1 4160110  
فاكس : +966 1 4604907

www.motabaqah.com.sa

المملكة العربية السعودية  
ص.ب 88458 الرياض 11662  
هاتف : +966 920029293  
فاكس : +966 920029296  
رقم العضوية : 174400  
السجل التجاري : 1010225110  
شركة مساهمة مقفلة برأس مال : 500.000.000 ر.س (مدفوع بالكامل)